

**BEST AVAILABLE COPY**

(19)

(11) Publication number:

02283646 A

Generated Document.

PATENT ABSTRACTS OF JAPAN(21) Application number: **01101594**(51) Intl. Cl.: **C04B 28/02**(22) Application date: **24.04.89**

(30) Priority:	(71) Applicant: SHIN ETSU CHEM CO LTD
(43) Date of application publication: 21.11.90	(72) Inventor: HAYAKAWA KAZUHISA NAKAMURA SHINICHIRO CHIBA TORU
(84) Designated contracting states:	(74) Representative:

**(54) CEMENT COMPOSITION
FOR EXTRUSION MOLDING**

(57) Abstract:

PURPOSE: To obtain the subject cement composition improved in shape retention by blending an inorganic additive containing cement with ground pulp fibers, an alkyl cellulose and/or hydroxylalkylalkyl cellulose and a formalin condensate of a specific allylsulfonate.

CONSTITUTION: 100 pts.wt. cement is blended with 10-60 pts.wt. inorganic additive such as silica sand to give an extrusion molding material. Then the molding material is blended with 3-15wt.% ground pulp fibers having 5-20µm diameter and 1-10mm length, 0.2-0.5wt.% alkyl cellulose and/or hydroxylalkylalkyl cellulose such as methyl cellulose or hydroxypropylmethyl cellulose having ≥ 800 cps viscosity in 2% aqueous solution at 20°C as a binder and 1/3-2 times as much an anionic surfactant such as formalin condensate of alkyl-substituted or nonsubstituted

allylsulfonate as the binder to give a
cement composition for extrusion
molding.

COPYRIGHT: (C)1990,JPO&Japio